



No. 0307/ 12471

To Elite Decor Co., Ltd.

The Department of Science Service presents the test report for the sample named "Light Weight Cornice" Laboratory No. L58/05622.1 as the total of 1 sample with reference to the request No. L58/05622 dated 1 October 2015.

Enclosed herewith the following result avails for your acknowledgement.

Department of Science Service

9 October 2015



Physics and Engineering Program

Tel. 0 2201 7130

Fax 0 2201 7127

E-mail : physics@dss.go.th



TEST REPORT

Sample's name

Light Weight Cornice

Mark / Brand

Buabau

Laboratory No.

L58/05622.1

Test Results

Compressive strength, MPa	0.26
Flexural strength, MPa	0.43
Initial surface absorption, $\text{mL}/(\text{m}^2/\text{s})$	
- at 10 minutes	0.02
- at 30 minutes	0.01
- at 60 minutes	0

Customer's name Elite Decor Co., Ltd.

Customer's address 964 Moo 4, Huatale, Nakhon Ratchasima 30000

Sample's description

1. Compressive strength : Light weight cornice size 100x100x100 mm, 2 pieces
2. Flexural strength : Light weight cornice size 100x50x400 mm, 3 pieces
3. Initial surface absorption : Light weight cornice size 100x100x100 mm, 1 piece

Test date 2 - 5 October 2015

Test method

1. Compressive strength : TIS. 1505-2541 (1998)
2. Flexural strength : ASTM C 1185-03
3. Initial surface absorption : BS 1881 : Part 208 : 1996

Approved by

Anon Pomprasit

(Mr. Anon Pomprasit)

Scientist, Senior Professional Level

Reported by

Kritsada Suttipan

(Mr. Kritsada Suttipan)

Scientist, Senior Professional Level