



No. 0307/ **14571**

To Elite Decor Co., Ltd.

The Department of Science Service presents the test report for the sample named "Light Weight Cornice" Laboratory No. L58/05642.1 as the total of 1 sample with reference to the request No. L58/05642 dated 2 October 2015.

Enclosed here with the following result avails for your acknowledgement.



Physics and Engineering Program

Tel. 0 2201 7130

Fax. 0 2201 7127

E-mail : physics@dss.go.th



กรมวิทยาศาสตร์บริการ

TEST REPORT

กรมวิทยาศาสตร์บริการ

Sample's name

Light Weight Cornice

Mark / Brand

Buabau

Laboratory No.

L58/05642.1

กรมวิทยาศาสตร์บริการ

Test Results

กรมวิทยาศาสตร์บริการ Accelerated weathering resistance for 1 week

Test cycle : 8 h UVA-340 at 60°C/4 h condensation at 50°C

- | | |
|--------------|-----------|
| - Cracking | Not found |
| - Blistering | Not found |
| - Chalking | Not found |

กรมวิทยาศาสตร์บริการ

กรมวิทยาศาสตร์บริการ

Customer's name Elite Decor Co., Ltd.

Customer's address 964 Moo 4, Huatale, Meuang, Nakhon Ratchasima 30000

Sample's description White sheet with the dimensions of approximately 6.0 × 12.0 × 0.3 cm

Test date 2-9 November 2015

Test method ASTM D 4329 (Cycle A)

Note Test equipment: QUV Accelerated weathering tester, Model QUV/SE

Approved by

Apinun Ubparakun

(Mr. Apinun Ubparakun)

Scientist, Senior Professional Level

Reported by

K. Sakulkaew

(Mr. Kartpan Sakulkaew)

Scientist, Senior Professional Level

กรมวิทยาศาสตร์บริการ

กรมวิทยาศาสตร์บริการ